

ION TREATED HYDROGEL

BACKGROUND OF THE INVENTION

[0001] This invention relates to a prosthetic intervertebral disc nucleus. More particularly it relates to an artificial disc nucleus made of a hydrogel material that exhibits a stable swelling pressure characteristic after implantation, i.e., the water content of the material and the size of the implant made from the material remains stable in vivo and also the time required to bring the material to a stable state prior to implantation can be reduced.

[0002] The intervertebral disc is a complex joint anatomically and functionally. It is composed of three component structures: the nucleus pulposus (the nucleus), the annulus fibrosus (the annulus) and the vertebral end-plates. The biochemical composition and anatomical arrangements within these component structures are related to the biomechanical function of the disc.

[0003] The nucleus occupies about 25-40% of the total disc cross-sectional area. It is primarily composed of mucoid material containing mainly proteoglycans with a small amount of collagen. The proteoglycans consist of a protein core with chains of negatively charged keratin sulphate and chondroitin sulphate covalently attached thereto. Due to these constituents, the nucleus is a loose hydrogel which usually contains about 70-90% water by weight. Although the nucleus plays an important role in the biomechanical function of the disc, the mechanical properties of the disc are not well known, largely because of the loose hydrogel nature of the nucleus.

[0004] As the nucleus is surrounded by the annulus and vertebral end-plates, and the negatively charged sulphate groups are immobilized due to the attachment of these groups to the polymer matrix, the matrix has a higher concentration of counter ions than its surroundings. This ion concentration results in a higher osmotic pressure than the

annulus e.g., ranging from about 0.1 to about 0.3 MPa. As a result of the high fixed charge density of the proteoglycan the matrix exerts an osmotic swelling pressure that can support an applied load in much the same way as air pressure in a tire supports the weight of a car.

[0005] It is the osmotic swelling pressure and hydrophilicity of the nucleus matrix that offers the nucleus the capability of imbibing fluid until it is balanced with the internal resistance stresses, resulting from the tensile forces of the collagen network, and the external stresses due to the loads that are applied by muscle and ligament tension. The swelling pressure (P_s) of the nucleus is directly dependent on the concentration and fixed charge densities of proteoglycan, i.e., the higher the concentration and fixed charge densities of proteoglycan the higher will be the swelling pressure of the nucleus. The external pressure changes with posture. When the human body is supine the compressive load on the third lumbar disc is 300 newtons (N) which rises to 700 N when an upright stance is assumed. The compressive load increases, yet again, to 1200 N when the body is bent forward by only 20°. Of course, the load is even higher under various physical activities.

[0006] When the external pressure (P_a) increases the previous balance, i.e., $P_s = P_a$, is upset. To reach a new balance the swelling pressure has to increase. This increase is achieved by increasing the proteoglycan concentration in the nucleus which is achieved by reducing the fluid in the nucleus. That is why discs lose about 10% of their height, as a result of creep, during the daytime. When the external load is released i.e., P_s is greater than P_a , the nucleus will imbibe fluid from its surroundings in order to reach the new equilibrium value. It is this property of the nucleus that is mainly responsible for the compressive properties of the disc.

1002033-103001

[0009] The intervertebral joint exhibits both elastic and viscous behavior. Hence, during the application of a load to the disc there will be an immediate "distortion" or "deformation" of the disc, often referred to as "instantaneous deformation." It has been reported that the major pathway by which water is lost, from the disc during compression, is through the cartilage end-plates. Since the water permeability of the end-plates is in the range of about 0.20 to about $0.85 \times 10^{-17} \text{ m}^4 \text{ N}^{-1} \text{ sec}^{-1}$ it is reasonable to assume that under loading, the initial volume of the disc is constant while the load is applied. Because the natural nucleus of the disc is in the form of a loose hydrogel, i.e., a hydrophilic polymeric material which is insoluble in water, it can be deformed easily, the extent of deformation of the disc being largely dependent on the extensibility of the annulus. It is generally believed that the hydrostatic behavior of the nucleus plays an important role in the normal static and dynamic load-sharing capability of the disc and the restoring force of the stretched fibers of the annulus balances the effects of the nucleus swelling pressure. Without the constraint by the annulus, annular bulging of the nucleus would increase considerably. If the load is maintained at a constant level, a gradual change in joint height, commonly referred to as "creep", will occur as a function of time. Eventually, the creep will stabilize and the joint is said to be in "equilibrium." When the load is removed the joint will gradually "recover" to its original height before loading. The creep and relaxation rates depend on the amount of load applied, the permeability of the end-plates and the water binding capability of the nucleus hydrogel. Creep and relaxation are essential processes in pumping fluid in and out of the disc.

[0010] Degeneration of the intervertebral disc is believed to be a common cause of final pathological changes and back pain. As the intervertebral disc ages it undergoes

degeneration. The changes that occur are such that, in many respects, the composition of the nucleus seems to approach that of the inner annulus. Intervertebral disc degeneration is, at least in part the consequence of compositional changes in the nucleus. It has been found that both the molecular weight and the amount of proteoglycans in the nucleus decrease with age, especially in degenerated discs, and the ratio of keratin sulphate to chondroitin sulphate in the nucleus to chondroitin sulphate and decrease in proteoglycan content decreases the fixed charged density of the nucleus from about 0.28 meq/ml to about 0.18-0.20 meq/ml. These changes cause the nucleus to lose part of its water binding capability which decreases the maximum swelling pressure it can exert. As a result, the maximum water content drops from over about 85%, in preadolescence, to about 70-75% in middle age. The glycosaminoglycan content of prolapsed discs has been found to be lower, and the collagen content higher, than that of normal discs of a comparable age. Discs L-4-L-5 and L-5-S-1 are usually the most degenerated discs.

[0011] It is known that although the nucleus only occupies about one third of the total disc area, it takes about 70% of the total loading in a normal disc. Thus, it has been found that the compressive load on the nuclei of moderately degenerated discs is about 30% lower than in comparable normal discs but the compressive load on the annulus increases by 100% in the degenerated discs. This load change is primarily caused by the structural changes in the disc as discussed above. The excess load on the annulus, of the degenerated disc, causes reduction of the disc height and excessive movement of the spinal segments. The flexibility of the disc produces excessive movement of the collagenous fibers which, in turn, injures the fiber attachments and causes delamination of the well-organized fibers of the annulus ring. The delaminated annulus can be further weakened by stress on the annulus and in severe cases this

stress will cause tearing of the annulus. This whole process is very similar to driving on a flat tire, where the reinforcement layer will eventually delaminate. Because the thickness of the annulus is not uniform, with the posterior portions being thinner than the anterior portions, delamination and lesions usually occur in the posterior area first.

[0012] The spinal disc may also be displaced or damaged due to trauma or diseases. In these cases, and in the case of disc degeneration, the nucleus may herniate and/or protrude into the vertebral canal or intervertebral foramen, in which case it is known as a herniated disc. This disc may in turn press upon the spinal nerve that exits the vertebral canal through the partially obstructed foramen, causing pain or paralysis in the area of its distribution. The most frequent site of occurrence of a herniated disc is in the lower lumbar region. A disc herniation in this area often involves the inferior extremities by compressing the sciatic nerve.

[0013] There are basically three types of treatment currently being used for treating low back pain caused by injured or degenerated discs: conservative care, discectomy and fusion. Each of these treatments has its advantages and limitations. The vast majority of patients with low back pain, especially those with first time episodes of low back pain, will get better with conservative care treatment. However, it is not necessarily true that conservative care is the most efficient and economical way to solve the low back pain problem.

[0014] Discectomy usually provides excellent short term results in relieving the clinical symptoms, by removing the herniated disc material, usually the nucleus, which causes the low back pain either by compressing the spinal nerve or by chemical irritation. Clearly, a discectomy is not desirable from a biochemical point of view. In a healthy

disc, the nucleus takes the most compressional load and in a degenerated disc this load is primarily distributed onto the annulus ring which, as described above, causes tearing and delamination of the annulus. Removal of the nucleus in a discectomy actually causes distribution the compressive load onto the annulus ring thereby narrowing the disc spaces. It has been reported that a long-term disc height decrease might be expected to cause irreversible osteoarthritis-like changes in the facet joint. That is why discectomy yields poor long-term benefits and results in a high incidence of reherniation.

[0015] Fusion generally does a good job eliminating symptoms and stabilizing the joint. However, because the motion of the fused segment is restricted, the range of motion of the adjoining vertebral discs is increased possibly enhancing their degenerative processes.

[0016] Because of these disadvantages, it is desirable to use a prosthetic joint device that not only is able to replace the injured or degenerated intervertebral disc, but also can mimic the physiological and the biochemical function of the replaced disc. Such a device would restore the normal functions of the disc and prevent further degeneration of the surrounding tissue.

[0017] Artificial discs are well known in the prior art. U.S. Patent No. 3,867,728, to Substad et al., relates to a device which replaces the entire disc. This device is made by laminating vertical, horizontal or axial sheets of elastic polymer. U.S. Patent No. 3,875,595 to Froning relates to a collapsible plastic bladder-like prosthesis of nucleus pulposus. U.S. Patent No. 4,309,777, to Patil, relates to a prosthesis utilizing metal springs and cups. A spinal implant comprising a rigid solid body having a porous coating on part of its surface is shown in Kenna's U.S. Patent No. 4,714,469. An intervertebral disc prosthesis consisting of a pair of rigid plugs to replace the degenerated disc is

referred by Kuntz, U.S. Patent No. 4,349,921. U.S. Patent No. 4,772,287 and 4,904,260 to Ray et al., relate to the use of a pair of cylindrical prosthetic intervertebral disc capsules with or without therapeutical agents. U.S. Patent No. 4,911,718, to Lee et al., relates to an elastomeric disc spacer comprising three different parts; nucleus, annulus and end-plates, of different materials. At the present time, none of these inventions has become a product in the spinal care market. Bao et al., in U.S. Patent No. 5,047,055 and 5,192,326 (assigned to the assignee of this invention and incorporated herein by reference) describe artificial nuclei comprising hydrogels in the form of large pieces shaped to conform to the shape of the disc cavity or beads within a porous envelope, respectively. The hydrogels have an equilibrium water content (EWC) of at least about 30% and a compressive strength of at least about 1 meganewtons per square meter (1 MNm^{-2}) when subjected to the constraints of the annulus and end plates of the disc. Preferably, the compressive strength of the nucleus is about 4 MNm^{-2} when measured as described in U.S. Patent Nos. 5,047,055 and 5,192,326.

[0018] A hydrogel is a network of a hydrophilic polymer(s) in which a large amount of water is present. In general, the water content is at least 20% by weight. In order to keep the hydrogel from being dissolved by the water, the polymer network must be crosslinked either physically or chemically. The water content (and therefore physical size) of hydrogels with either or both types of crosslinks may be sensitive to a variety of environmental conditions depending on the polymer. These environmental conditions include pH, temperature, electric field, and ionic strength & type.

[0019] Physically crosslinked hydrogels are semi-crystalline forms of the polymeric material. The crystalline domains are locations where the polymer chains are neatly packed. The crystalline domains are suspended in

1002023-103001

the amorphous (*i.e.*, loosely packed, unordered) regions of the polymer, and in order for the crystalline domains to grow they must pull polymer chains from the amorphous regions. As the material becomes more crystalline the equilibrium water content is reduced. The material will continue to become more crystalline until the mobility of the polymer chains in the amorphous regions of the polymer is reduced to the point that they cannot be drawn into the crystalline structure. At this point the polymeric material has reached its equilibrium crystallinity. When using a hydrogel material in an implant, it can be advantageous to ensure that the polymeric material has reached its equilibrium crystallinity prior to being placed *in vivo* so that the material properties and size are stable.

[0020] Certain types of ions can help to increase the rate at which polymer chains in the amorphous regions of the material are drawn into the crystalline regions. The ions that have the greatest effect will depend on the type of polymer. In addition, a greater concentration of ions may increase the rate of crystalline growth. In the case of PVA, potassium has a greater effect than sodium on the rate of crystallinity (as measured by mass change) when comparing cations. The carbonate ion has a greater effect than chloride when comparing anions. Therefore, potassium carbonate should have a greater effect than sodium chloride on the rate at which a PVA hydrogel will reach its equilibrium crystallinity.

[0021] Due to the high water content of hydrogels, there has been interest in using these materials in a variety of medical devices. These devices include those intended for both short (such as a cervical dilator) & long term (such as a non-throbogenic coating for vascular grafts) exposure to the body, and also both load bearing (such as an artificial articular cartilage) and non-load bearing devices (such as contact lenses).

10020339 0300
FOOT 62200

[0022] The primary disadvantage of the inventions of Stubstad et al., Patil, Kenna and Lee et al. is that use of their prostheses requires complete replacement of the natural disc which involves numerous surgical difficulties. Secondly, the intervertebral disc is a complex joint, anatomically and functionally, comprising the aforementioned three component structures, each of which has its own unique structural characteristics. Designing and fabricating such a complicated prosthesis from acceptable materials, which will mimic the function of the natural disc, is very difficult. A further problem is the difficulty of preventing the prosthesis from dislodging. Fourthly, even for prostheses which are only intended for replacing the nucleus, a major obstacle has been to find a material which is similar to the natural nucleus and is also able to restore the normal function of the nucleus.

[0023] Hydrophobic elastomers and thermoplastic polymers are not desirable for use in the prosthetic nuclei due to their significant inherent differences from the natural nucleus e.g., lack of hydrophilicity, in the elastomers, and lack of flexibility in the thermoplasts.

[0024] These problems are not solved by Kuntz, who uses elastic rubber plugs, or by Froning and Ray et al., who use bladders or capsules, respectively, which are filled with a fluid or thixotropic gel. According to the Ray and Froning patents, liquid was used to fill the capsules and bladders, respectively, thereby requiring that their membranes be completely sealed to prevent fluid leakage. As a consequence, those devices cannot completely restore the function of the nucleus which allows body fluid to diffuse in and out during cyclic loading thereby providing the nutrients the disc needs.

[0025] The Bao et al. prosthetic lumbar disc nuclei are made from hydrogels. Hydrogels have been used in biomedical applications, such as contact lenses. Among the advantages

of hydrogels is that they are more biocompatible than hydrophobic elastomers and metals. This biocompatibility is largely due to the unique characteristics of hydrogels in that they are soft and contain water like the surrounding tissues and have relatively low frictional coefficients with respect to the surrounding tissues. The biocompatibility of hydrogels results in prosthetic nuclei which are more easily tolerated in the body. Furthermore, hydrophobic elastomeric and metallic gels will not permit diffusion of aqueous compositions, and their solutes, therethrough.

[0026] An additional advantage of some hydrogels is their good mechanical strength which permits them to withstand the load on the disc and restore the normal space between the vertebral bodies. The aforementioned nuclei of Bao et al. have high mechanical strength and are able to withstand the body loads and assist in the healing of the defective annuli.

[0027] Other advantages of the hydrogels, used in the Bao et al. nuclei, are their excellent viscoelastic properties and shape memory. Hydrogels contain a large amount of water which acts as a plasticizer. Part of the water is available as free water which has more freedom to leave the hydrogel when the hydrogel is partially dehydrated under mechanical pressure. This characteristic of the hydrogels enables them to creep, in the same way as the natural nucleus, under compression, and to withstand cyclic loading for long periods without any significant degradation or loss of their elasticity. This is because water in the hydrogel behaves like a cushion whereby the polymeric network of a hydrogel with a high EWC is less susceptible to damage under mechanical load.

[0028] Another advantage of hydrogels is their permeability to water and water-soluble substances, such as nutrients, metabolites and the like. It is known that body fluid diffusion, under cyclic loading, is the major source of nutrients to the natural disc. If the route of this nutrient

diffusion is blocked, e.g., by a water-impermeable nucleus, further deterioration of the disc will ensue.

[0029] Hydrogels can be dehydrated and hydrated again. When a hydrogel is dehydrated, its volume decreases, thereby facilitating implantation of the prosthetic nucleus into the nuclear cavity in the disc. The implanted prosthetic nucleus will then swell, in the body, by absorption of body fluid up to its EWC. Alternately, the device may be inserted into the disc at its approximate *in vivo* equilibrium water content for the expected lumbar intradiscal pressure for the patient. The equilibrium water content will vary depending on the position of the patient during implantation. The patient is positioned differently depending on whether the anterior, lateral or posterior approach is used by the surgeon for implanting the hydrogel nucleus.

[0030] The EWC of the hydrogel is adjusted to match the anticipated pressure on the implant at implantation so the EWC does not change after implantation. The EWC of a hydrogel depends on the compressive load applied thereto. Thus, the EWC of a specific hydrogel in an open container will differ from the EWC of the same hydrogel in a closed vessel such as an intervertebral disc. The EWC values, referred to below, are for hydrogels subjected to compressive loads under the conditions found in an intervertebral disc. The expansion factor of a dehydrated hydrogel, in turn, is dependent on its EWC. Thus, it may vary from 1.19 for a hydrogel of 38% EWC to 1.73 for a hydrogel of 80% EWC. For an 80% EWC hydrogel, the volume of the dehydrated prosthetic nucleus is usually about 20% of that of the hydrated one. The ability to be dehydrated and then return to its original shape upon hydration, up to its EWC, makes it possible to implant the device posterior-laterally, during surgery, thereby reducing the complexity and risk of intraspinal surgery as traditionally used. The danger of perforation of the nerve, dural sac, arteries and other organs is also

reduced. In addition, the incision area on the annulus can be reduced, thereby helping to heal the annulus and prevent the reherniation of the disc. Hydrogels are also useful for drug delivery into the disc due to their capability for controlled release of drugs. Various therapeutic agents, such as growth factors, long term analgesics, antibiotics and anti-inflammatory agents can attach to the prosthetic nucleus and be released in a controllable rate after implantation of the nucleus in the disc.

[0031] Furthermore, dimensional integrity can be maintained with hydrogels having a water content of up to about 90%. This dimensional integrity, if the nucleus is properly designed, will aid in distributing the vertebral load to a larger area on the annulus ring and prevent the prosthetic nucleus from bulging and herniating.

SUMMARY OF THE INVENTION

[0032] It is an object of this invention to provide a method for forming a high strength hydrogel implant which exhibits a constant swelling pressure profile (water content change with respect to applied pressure) immediately upon implantation in a dehydrated state. It is a further object of the invention to provide an artificial nuclear implant which has stable swelling pressure characteristics immediately after implantation and onward. It is yet another object of the invention to provide a method for providing an artificial nuclear implant which maintains a uniform disc spacing based on disc loading after implantation at all times after implantation.

[0033] These and other objects are achieved by a method for forming a high strength hydrogel medical implant which includes preparing a hydrogel solution, injecting the solution into a mold and causing the molded solution to gel. The molded gel is then washed in a physiologic solution such as a saline solution for between two to twelve weeks. The saline solution may contain between .025 M and .25 M and

preferably between .025 M and .05 M solution of potassium carbonate (K_2CO_3). Besides a solution containing potassium carbonate any physiologic solution having an ionic charge could be used, for example, serum at a Ph that would allow some or all proteins to be charged. After the hydrogel solution has been washed from between two to twelve weeks, it is dehydrated and packaged. By dehydration, it is meant that the water content of the hydrogel is reduced to about 55%. The saline solution used is preferably a .9% phosphate buffered sodium chloride solution to which the potassium carbonate is added at a concentration of between .025M and .25M.

[0034] The washing process may run from one (1) day to twelve (12) weeks and preferably from two (2) to twelve (12) weeks and most preferably for twelve (12) weeks.

[0035] The saline solution is changed regularly, for example, two, three, five or more times a week during the washing process. In addition, the concentration of the potassium carbonate solution can be changed during the washing period with a more concentrated .05 M solution being used during the first 2 to 4 weeks and then a lower concentration solution of about .025 M potassium carbonate being used for the last 4 to 8 weeks of washing. Normally, the hydrogel is irradiated after washing in a hydrated state of about 75% water content.

[0036] It has been found that washing the hydrogel implants after gelation in a physiologic saline rather than water ensures that the swelling pressure characteristics of the material used in the artificial nucleus implant would remain stable after implantation. Results showing that washing the implants in saline creates a hydrogel material that does not undergo swelling pressure property changes *in vivo*.

[0037] One of the most important properties of any load-bearing hydrogel implant is the swelling pressure

characteristic (i.e. water content vs. externally applied pressure) of the material used in the implant. Early results from a pre-clinical safety studies have shown that the swelling pressure characteristics of the water-washed PVA hydrogel was not constant during the first 4 weeks in vivo, with no further changes occurring at later time points. These changes indicate that the implant may have a lower in vivo equilibrium water content immediately after implantation than originally estimated, and would therefore have a smaller volume. This reduction in implant volume would have no bearing on the safety of the device, but could have an effect on the ability of the implant to maintain disc height. Maintenance of disc height is a parameter that may be assessed in a clinical study to evaluate efficacy of the implant.

BRIEF DESCRIPTION OF THE DRAWINGS

[0038] FIG. 1 shows that water-washed implants that have been implanted into the disc space will have a lower water content than control implants when subjected to 1.1 MPa of osmotic pressure. The figure shows that less than one month of exposure to the physiologic environment is responsible for this result and no further changes occur at later time points;

[0039] FIG. 2 shows that saline-washed implants (which have been pre-exposed to a physiologic environment prior to implantation) that have been implanted into the disc space will have a similar water content to control implants when subject to 1.1 MPa of osmotic pressure;

[0040] FIG. 3 is a process flow chart for forming the spinal nucleus of the present invention; and

[0041] FIG. 4 is a chart showing the weight change versus time with three different wash solutions.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0042] One of the most important properties of any load-bearing hydrogel implant is the swelling pressure

characteristic of the material used in the implant. The swelling pressure characteristic of a hydrogel describes the relationship between applied load and equilibrium water content. In general, a larger load on the material will result in a reduced water content. This phenomenon has been well documented for the nucleus pulposus of the intervertebral disc, which is a hydrogel.

[0043] It is important for any load-bearing implant made from a hydrogel material to have a stable swelling pressure characteristic after implantation. If the swelling pressure characteristic of the implant changes over time it may be difficult to predict the equilibrium water content and size of the implant. Early results from a pre-clinical safety study evaluating an artificial nucleus pulposus implant made from a water-washed poly (vinyl alcohol) (PVA) hydrogel showed that the swelling pressure characteristic had changes compared to an unimplanted control after 4 weeks *in vivo*, with no further changes occurring at later time points.

[0044] Washing the implants after gelation in a physiologic saline solution rather than water was adopted in order to ensure that the swelling pressure characteristics of the material used in the artificial nucleus implant would remain stable after implantation. This change to the method used to process the material was successful as shown in FIGS. 1 and 2. The results of washing the implants in saline on the swelling pressure characteristic can be seen at the one-month time point, and are merely confirmed by results from later time points.

[0045] Example 1

[0046] The implants used in this study were fabricated in a class 1,000 clean room using the manufacturing flow chart of Fig. 3. The implants were made from a 98.5% hydrolyzed (PVA-117, Kuraray, Japan) poly (vinyl alcohol) (PVA) hydrogel that is physically crosslinked through the use of a freezing-thawing technique. Any water used in the fabrication of the

1000333-10001
FOUO "SECRET"

device was USP Sterile Water-for-Injection (WFI) (Abbott Laboratories, North Chicago, IL). All of the implants tested were washed for twelve weeks in 0.9% phosphate buffered saline (PBS) (cat. #1000-3, Sigma Diagnostics, St. Louis, MO) with 50 mM potassium carbonate (SigmaUltra, cat. #P-5833, Sigma Chemical Co., St. Louis, MO) for the first 4 weeks of the wash cycle. The implants were then washed in PBS plus 25 mM potassium carbonate for the last 8 weeks of the wash cycle. The implants were sterilized with 25-35 kGy of gamma sterilization and implanted at their approximate *in vivo* equilibrium water content which was at approximately 55% water content.

[0047] The PVA hydrogel material submitted for irradiation had approximately 80% water content. Due to irradiation induced crosslinking the material had about 78% water content after sterilization. After subsequently being dehydrated to 55% water content the maximum hydration level upon rehydration is about 75% water content. A comparison of the ionic concentration of the 25 mM K₂CO₃ wash solution (assuming full dissociation) and human plasma is shown in Table I.

[0048] The PBS and potassium carbonate washing solutions were heated to 37°C and the solutions were changed five times a week for the first two weeks and two or three times a week thereafter. The solution changes were required to reduce bioburden.

Table I
Ionic Concentration (mM) of the Final Saline Wash Solution
and Human Plasma

	Na ⁺	K ⁺	Ca ⁺²	Mg ⁺²	Cl ⁻	HCO ₃ ⁻ CO ₃ ⁻²	H ₂ PO ₄ ⁻ HPO ₄ ⁻²	SO ₄ ⁻²
Human Plasma	142	5	2.5	1.5	103	27	1	0.5
Wash Solution	137	54.2	0	0	122.7	25	10	0

[0045] A test designed to show the effects of different wash solutions on a PVA hydrogel was performed. In this test

three different wash solutions were evaluated: [1] USP water for injection (WFI); [2] 0.9% phosphate buffered sodium chloride in WFI (saline), and [3] the saline plus 25 mM potassium carbonate. The effect of the wash solution was determined by weighing the test samples. As the hydrogel becomes more crystalline, the polymer chains become more tightly packed, and the material can hold less water and will therefore have less mass (other tests have been performed which shows that the mass loss is not due to polymer washing out of the material). The results from first 13 weeks of this test are shown in FIG. 4.

[0046] By properly selecting the wash solution to which the hydrogel material is exposed, the processing time required for it to reach equilibrium could be reduced. In addition, an intermediate dehydration step (such as halfway through the wash cycle) may be performed to enhance cross-link formation and reduce overall wash time.

[0047] Although the invention herein has been described with reference to particular embodiments, it is to be understood that these embodiments are merely illustrative of the principles and applications of the present invention. It is therefore to be understood that numerous modifications may be made to the illustrative embodiments and that other arrangements may be devised without departing from the spirit and scope of the present invention as defined by the appended claims.